



Aerosol and Touch up Clearcoat Lacquer

Description

One component acrylic clearcoat which can be applied over most suitably prepared basepaints. Easy application, fast drying, non-yellowing, easy to polish.

Application

Any gloss surfaces must be lightly rubbed down with 1200 before application.
Number of coats: 2 – 3

Drying Times

(Air drying at 20°C)

Dust free 3 – 5 mins

Tack free 15-20 mins

Through drying: 6 hours Interval between coats: 10 mins

Polishing: after 24 hours at room temperature. The complete hardening occurs in the following 3-4 days.

NOTES

Aerosol and touch up clearcoat lacquer is not gasoline proof. It is suitable for all motorbike parts, except for the tank. For gasoline proof lacquer, please see our 2K gloss Isocyanate free clearcoat for spray gun application.

The painted substrate must not be exposed to severe conditions in the first days after the painting. Until fully cured, strong humidity condensations, like dew and frost and contact with aggressive agents like smog, detergents and salt on the roads must be avoided.